



nomalen® 70N

<u>Property</u>	<u>Typical value</u>	<u>Norm</u>
Density	70 kg/m ³	DIN 53420
Tensile Strength //	78 N/cm ²	ISO 1798
Tensile Strength ⊥	71 N/cm ²	ISO 1798
Elongation //	171 %	ISO 1798
Elongation ⊥	162 %	ISO 1798
Compressive Strength, deflection 25%	113 kPa	ISO 3386
Compressive Strength, deflection 50%	210 kPa	ISO 3386
Water absorption 24h	<1 vol.-%	DIN EN 12087
Recommended working temperature	-50 - +95°C	
Thermal conductivity	on request	
Fire behaviour	on request	

This information is based on our actual knowledge. However, it does not constitute a guarantee of our product's characteristics and does not engage in any case our liability.

NMC Termonova Oy

Torppanummentie 44, FI-10210 Inkoo, Finland,
Tel.: + 358 (0)207 809600, Fax: + 358 (0)207 809601, e-mail: info@termonova.fi, www.termonova.fi
Y-tunnus/ FO-nummer/ business ID 0114914-9 ALV/Moms/ VAT FI01149149

